

PRODUCT DATA SHEET

SikaPlast®-2008 AP

HIGH PERFORMANCE SUPERPLASTICISER

DESCRIPTION

SikaPlast®-2008 AP universal and effective superplasticizer, possessing the properties of moderator of setting a concrete mixture with the possibility of increasing the transportation time.

USES

SikaPlast®-2008 AP is especially suitable for the production of ready mixed and site batched concrete with normal transportation times and workability requirements, high water reduction and improved flow characteristics.

SikaPlast®-2008 AP is recommended for the following:

- concrete with reduced amount of fines or difficult aggregates;
- concrete with extended transportation and workability requirements;
- high performance concrete;
- concrete with enhanced workability requirements due to a high content of blended cements.

CHARACTERISTICS / ADVANTAGES

SikaPlast®-2008 AP is a powerful superplasticiser which acts through several different mechanisms including surface adsorption and sterical effects separating the cementitious binder particles. The following advantageous properties are achieved:

- keeps extended workability time with many difficult cements despite high water reduction;
- superior plasticising effect, resulting in improved flow, placing and compaction characteristics;
- water reduction, resulting in improved density, higher strength and reduced permeability;
- reduced tendency to shrinkage and creep;
- reduced carbonation of the concrete;
- improved cohesion of the concrete.

SikaPlast®-2008 AP does not contain chlorides or any other ingredients which promote the corrosion of steel. It is therefore suitable for use in reinforced and prestressed concrete structures.

PRODUCT INFORMATION

Chemical base	Modified polycarboxylate
Packaging	Non returnable 200 l drums, 1000 l containers, Bulk supply on demand
Appearance / Colour	Brown liquid
Shelf life	12 months from date of production if stored properly in undamaged, unopened, original sealed packaging.
Storage conditions	Storage at temperatures between +5°C and +30°C. Protect from direct sunlight, frost and contamination.
Density	1,065±0,02 kg/l (at +20°C)

TECHNICAL INFORMATION

Concreting Guidance

The standard rules of good concreting practice, concerning production and placing, are to be followed. Fresh concrete must be cured properly and curing applied as early as possible. Laboratory trials shall be carried out before concreting on site, especially when using a new mix design or producing with new concrete components.

APPLICATION INFORMATION

Recommended Dosage

0,2 - 2,5 % by weight of cement/binder.

Compatibility

SikaPlast®-2008 AP may be combined with many other Sika products. Important: Always conduct trials before combining products in specific mixes and contact Sika Technical Service for more information and advice.

Dispensing

SikaPlast®-2008 AP is added to the gauging water or added with it into the concrete mixer. To take advantage of the workability enhancing ability, a wet mixing time, which is depending on the mixing conditions and mixer performance, of at least 60 seconds is recommended. To avoid excess water in the concrete, the final dosage must begin only after 2/3 of the wet mixing time.

Restrictions

SikaPlast®-2008 AP shall not be added to dry cement.

APPLICATION INSTRUCTIONS

DISPENSING

For storage in tanks always use cleaned tanks and clean and disinfect them minimum once a year. If frozen, SikaPlast®-2008 AP may be used after thawing slowly at room temperature following intensive remix. Retarding according to dosage. Excessive water addition or overdosing may cause bleeding or segregation. Formwork pressure: due to strong plasticising effect and long opentime concretes with SikaPlast®-2008 AP can cause extended formwork pressure. Preliminary trials are a must.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Services AG
Tüffenwies 16
8048 Zürich
Tel: +41 58 436 4040
www.sika.com



PRODUCT DATA SHEET
SikaPlast®-2008 AP
June 2018, Version 01.0
021301011000003022

SikaPlast-2008AP-en-(06-2018)-1.pdf

